

**PRODUCT DESCRIPTION:** FIBERGLASS MESH :4510050

The standards are according to GB/T1871--2001 and results shown below are obtained on the material referenced which required test procedure and frequency.

PROPERTIES 性能	STANDARD 标准	RESULT OF TEST 测试结果
<b>WARP RAW YARN(TEX)</b> 径向纱线 tex	67*2	67.2*2
<b>WEFT RAW YARN(TEX)</b> 纬向纱线 tex	150	152
<b>WARP(MESH/MM)</b> 径向	5±0.25	5.12
<b>WEFT(MESH/MM)</b> 纬向	5±0.25	5.1
<b>WEIGHT(G/M2)</b> 克重	45 ± 3.75	43.8
<b>WARP TENSILE STRENGTH ( N/50MM)</b> 径向拉力强度	525	530
<b>WEFT TENSILE STRENGTH (N/50MM)</b> 纬向拉力强度	650	701

Fiberland is hereby certifies that results have been obtained from sample of products anyhow minor alteration in results could be observed basis on index errors.

