



# Niko bind

## NIKOBIND 2320

### Hydroxylated saturated polyester resin

- **Application:** automotive O.E.M. stoving clear coat, to be used in combination with alkylated melamine formaldehyde resins.
- **Characteristics:** provides improved optical properties for the clear coat, adjusts the overall reaction speed of the clear coat resins and as a result a smoother baking process is achieved.
- **Solid content:** 75%±2
- **Acid value:** (mgKOH/g): 13 - 14
- **Viscosity:** (Poise at 25°C): 50 - 55
- **Hydroxyl value:** (mgKOH/g): 40 - 50
- **Solvent:** solvesso-100/n-butanol: 90 / 10